

**AMENDMENTS TO THE CLAIMS**

1. (Original) A method of forming a negative pattern of carbon nanotubes which comprises the steps of:

(a) providing surface-modified carbon nanotubes by introducing double bond-containing functional groups into the surface of the carbon nanotubes;

(b) dispersing the surface-modified carbon nanotubes in an organic solvent along with a photoinitiator to obtain a liquid coating composition;


(c) applying the liquid coating composition to a substrate and evaporating the organic solvent by prebaking to provide a coating film on the substrate;

(d) exposing the coating film to UV light through a photomask having a desired pattern to induce photo-polymerization of the carbon nanotubes in the exposed areas of the coating film; and

(e) developing the coating film with an organic developer to remove unexposed areas of the coating film and to obtain a negative pattern of the carbon nanotubes.


2. (Original) The method according to claim 1, wherein the double bond-containing functional group is introduced from a compound having a structure of Formula 1 or Formula 2:

## Formula 1



(wherein, R<sub>1</sub> is H or CH<sub>3</sub>; and X is Cl, NH<sub>2</sub> or OH); and

## Formula 2



(wherein, R<sub>1</sub> is H or CH<sub>3</sub>; A is C<sub>1</sub>~C<sub>6</sub> alkylene or  $\text{R}_2-\overset{\text{O}}{\parallel}{\text{C}}$  (in which R<sub>2</sub> is direct bond or C<sub>1</sub>~C<sub>6</sub> alkylene) ; and X is Cl, NH<sub>2</sub> or OH).

3. (Original) The method according to claim 1, wherein the carbon nanotubes are produced by an arc discharge method, a laser ablation method, a high temperature filament plasma chemical vapor deposition method, a microwave plasma chemical vapor deposition method, a thermochemical vapor deposition method or a thermal decomposition method.


4. (Original) The method according to claim 1, wherein the photoinitiator is selected from the group consisting of an acetophenone-based photoinitiator, a benzoin-based photoinitiator, a benzophenone-based photoinitiator, a

thioxantone-based photoinitiator, a special grade photoinitiator and a copolymerizable photoinitiator.

5. (Original) The method according to claim 4, wherein the special grade photoinitiator is selected from the group consisting of 1-phenyl-1,2-propanedione-2-(O-ethoxycarbonyl)oxime, 2,4,6-trimethyl benzoyl diphenyl phosphine oxide, methyl phenylglyoxylate, benzil, 9,10-phenanthraquinone, camphorquinone, dibenzosuberone, 2-ethylanthraquinone, 4,4'-diethylisophthalophenone and 3,3',4,4'-tetra(t-butylperoxycarbonyl)benzophenone.


6. (Original) The method according to claim 4, wherein the copolymerizable photoinitiator is selected from the group consisting of compounds of Formulas 3 to 6:

Formula 3




(wherein, R = (meth)acryl group);


Formula 4



Formula 5



Formula 6



7. (Currently Amended) The method according to claim 1, wherein the substrate is selected from the group consisting of a glass substrate, a ~~silicone~~ silicon substrate and a plastic substrate.

8. (Original) The method according to claim 1, wherein the liquid coating composition further comprises a co-photoinitiator.

9. (Currently Amended) The method according to claim 8, wherein the co-photoinitiator is selected from the group consisting of triethanolamine, methyldiethanolamine, triisopropanolamine, 4,4'-dimethylamino

benzophenone, 4,4'-diethylamino benzophenone, 2-dimethylamino ethylbenzoate, 4-dimethylamino ethylbenzoate, ~~2-n-butoxyethyl-4-dimethylaminobenzoate~~ 2-n-butoxyethyl-4-dimethylaminobenzoate, 4-dimethylamino isoamylbenzoate, 4-dimethylamino-2-ethylhexyl benzoate and Eosin Y.

10. (Original) The method according to claim 1, wherein the liquid coating composition further comprises co-polymerizable monomers or oligomers containing double bonds for the carbon nanotubes to copolymerize with the monomers or oligomers during the photo-polymerization step (d).

11. (Original) The method according to claim 1, wherein the liquid coating composition further comprises polymers or oligomers free of double bonds, as a coating binder.